



Whether for concise memos, impressive presentations or expressive flyers, MAESTRO® color deliver brilliant full-colour results every time. MAESTRO® color – the multifaceted way to communicate.



Technical Data: MAESTRO color 80 g/m²

Grammage		g/m ²	ISO 536		80 ± 3.0
Caliper		mm/1000	ISO 534		103 ± 4
Stiffness L&W	MD	mN	ISO 2493	min	100
Stiffness L&W	CD	mN	ISO 2493	min	50
Roughness Bendtsen		ml/min	ISO 8791-2		210 ± 50
Porosity		ml/min	ISO 5636-3		850 ± 450
Abrasion		mg	DIN 53 109	max	10
Moisture		%	ISO 287		4.8 ± 0.5

Product meets EN 12281, requirements for copy paper for dry toner imaging processes. Production processes certified according to ISO 9001, 14001 and 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA

TECHNICAL CUSTOMER SERVICE

19.12.2007



Whether for concise memos, impressive presentations or expressive flyers, MAESTRO® color deliver brilliant full-colour results every time. MAESTRO® color – the multifaceted way to communicate.



Technical Data: MAESTRO color 80 g/m²

Grammage		g/m ²	ISO 536		80 ± 3.0
Caliper		mm/1000	ISO 534		103 ± 4
Stiffness L&W	MD	mN	ISO 2493	min	100
Stiffness L&W	CD	mN	ISO 2493	min	50
Roughness Bendtsen		ml/min	ISO 8791-2		210 ± 50
Porosity		ml/min	ISO 5636-3		850 ± 450
Abrasion		mg	DIN 53 109	max	10
Moisture		%	ISO 287		4.8 ± 0.5

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, 14001 and 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA

TECHNICAL CUSTOMER SERVICE

06.03.2008



Whether for concise memos, impressive presentations or expressive flyers, MAESTRO® color deliver brilliant full-colour results every time. MAESTRO® color – the multifaceted way to communicate.



Technical Data: MAESTRO color 80 g/m²

Grammage		g/m ²	ISO 536		80 ± 3.0
Caliper		mm/1000	ISO 534		103 ± 4
Stiffness L&W	MD	mN	ISO 2493	min	100
Stiffness L&W	CD	mN	ISO 2493	min	50
Roughness Bendtsen		ml/min	ISO 8791-2		210 ± 50
Porosity		ml/min	ISO 5636-3		850 ± 450
Abrasion		mg	DIN 53 109	max	10
Moisture		%	ISO 287		4.8 ± 0.5

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, 14001 and 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA

TECHNICAL CUSTOMER SERVICE

06.03.2008



Whether for concise memos, impressive presentations or expressive flyers, MAESTRO® color deliver brilliant full-colour results every time. MAESTRO® color – the multifaceted way to communicate.



Technical Data: MAESTRO color 80 g/m²

Grammage		g/m ²	ISO 536		80 ± 3.0
Caliper		mm/1000	ISO 534		103 ± 4
Stiffness L&W	MD	mN	ISO 2493	min	100
Stiffness L&W	CD	mN	ISO 2493	min	50
Roughness Bendtsen		ml/min	ISO 8791-2		210 ± 50
Porosity		ml/min	ISO 5636-3		850 ± 450
Abrasion		mg	DIN 53 109	max	10
Moisture		%	ISO 287		4.8 ± 0.5

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper.
Production processes certified according to ISO 9001, 14001 and 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA

TECHNICAL CUSTOMER SERVICE

06.03.2008



Whether for concise memos, impressive presentations or expressive flyers, MAESTRO® color deliver brilliant full-colour results every time. MAESTRO® color – the multifaceted way to communicate.



Technical Data: MAESTRO color 160 g/m²

Grammage	g/m ²	ISO 536		160 ± 6.0
Caliper	mm/1000	ISO 534		214 ± 6
Roughness Bendtsen	ml/min	ISO 8791-2		210 ± 50
Porosity	ml/min	ISO 5636-3		650 ± 350
Abrasion	mg	DIN 53 109	max	15
Moisture	%	ISO 287		4.8 ± 0.5

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, 14001 and 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA

TECHNICAL CUSTOMER SERVICE

06.03.2008



Whether for concise memos, impressive presentations or expressive flyers, MAESTRO® color deliver brilliant full-colour results every time. MAESTRO® color – the multifaceted way to communicate.



Technical Data: MAESTRO color 160 g/m²

Grammage	g/m ²	ISO 536		160 ± 6.0
Caliper	mm/1000	ISO 534		214 ± 6
Roughness Bendtsen	ml/min	ISO 8791-2		210 ± 50
Porosity	ml/min	ISO 5636-3		650 ± 350
Abrasion	mg	DIN 53 109	max	15
Moisture	%	ISO 287		4.8 ± 0.5

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, 14001 and 18001.

SIGINIFICANCE OF VALUES: 2 SIGMA

TECHNICAL CUSTOMER SERVICE

06.03.2008



Whether for concise memos, impressive presentations or expressive flyers, MAESTRO® color deliver brilliant full-colour results every time. MAESTRO® color – the multifaceted way to communicate.



Technical Data: MAESTRO color 160 g/m²

Grammage	g/m ²	ISO 536		160 ± 6.0
Caliper	mm/1000	ISO 534		214 ± 6
Roughness Bendtsen	ml/min	ISO 8791-2		210 ± 50
Porosity	ml/min	ISO 5636-3		650 ± 350
Abrasion	mg	DIN 53 109	max	15
Moisture	%	ISO 287		4.8 ± 0.5

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, 14001 and 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA

TECHNICAL CUSTOMER SERVICE

06.03.2008