



Color Copy coated silk has a coating specially adapted to digital colour laser printing which gives the paper an elegant satin quality. These features are not only pleasing to the eye but also pleasant to the touch and enhance the overall impression of annual reports, brochures and flyers.



**Technical Data:** Color Copy coated silk

<b>Grammage</b>	g/m <sup>2</sup>	ISO 536
<b>Caliper</b>	mm/1000	ISO 534
<b>Opacity</b>	%	ISO 2471
<b>Moisture</b>	%	ISO 287
<b>Brightness with UV</b>	D65 %	ISO 2470
<b>CIE Whiteness*)</b>		ISO 11475
<b>Gloss 75°</b>		TAPPI T 48
<b>Formation</b>	Techpap	

	<b>135</b>	<b>170</b>	<b>200</b>	<b>250</b>
	<b>135</b> ± 3.0	<b>170</b> ± 4.0	<b>200</b> ± 6.0	<b>250</b> ± 8.0
	<b>110</b> ± 4	<b>150</b> ± 6	<b>188</b> ± 7	<b>234</b> ± 10
	<b>min 94.0</b>	<b>min 96.0</b>	<b>min 98.0</b>	<b>min 99.0</b>
	<b>4.8</b> ± 0.6	<b>4.8</b> ± 0.6	<b>4.8</b> ± 0.6	<b>4.8</b> ± 0.6
	<b>102.0</b> ± 2.0	<b>102.0</b> ± 2.0	<b>102.0</b> ± 2.0	<b>102.0</b> ± 2.0
	<b>139</b> ± 2.5	<b>139</b> ± 2.5	<b>139</b> ± 2.5	<b>139</b> ± 2.5
	<b>55</b> ± 4	<b>55</b> ± 4	<b>55</b> ± 4	<b>55</b> ± 4
	<b>max 30</b>	<b>max 30</b>	<b>max 30</b>	<b>max 30</b>

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001.

SIGNIFICANCE OF VALUES: 2 SIGMA